



62.5/125 Graded-Index Optical Fiber

P/N: BF04431-01

Product Overview

This fiber features a 62.5 μm core and a 125 μm silica cladding. The fiber coating is a 245 μm dual UV acrylate. 62.5 μm fiber is typically recommended for applications where high bandwidth and operability at 1300 nm is specified. The fiber can use either LED or laser light sources.

Typical Applications

- Industrial Data Communications
- Local-Area Networks

Product Specifications	
Product Description	62.5/125 Graded-Index Optical Fiber
Physical Characteristics	
Coating Material	Dual UV Acrylate
Core Diameter	62.5 ± 2.5 µm
Cladding Diameter	125 ± 1 µm
Coating Diameter	245 ± 10 µm
Core/Clad Offset	≤ 1 µm
Core Non-Circularity	≤ 5%
Clad Non-Circularity	≤ 1.0%
Crimp & Cleave Compatible	No
Optical Characteristics	
Type	Multimode Graded-Index
Numerical Aperture	0.275
Bandwidth @ 1300 nm	≥ 500 MHz-km
Bandwidth @ 850 nm	≥ 200 MHz-km
Attenuation @ 1300 nm	≤ 0.6 dB/km
Attenuation @ 850 nm	≤ 2.9 dB/km
Mechanical and Environmental	
Operating Temperature	-60 to +85 °C
Short-Term Bend Radius	≥ 10 mm
Long-Term Bend Radius	≥ 17 mm
Proof Test Level	100 kpsi (0.689 GPa)
Order by Part Number	BF04431-01
Product Description Code	ACU-MD062C
OPTIONS	Cabling, Connectorization, Metalization
NOTE	Lightera polyimide optical fibers are known to operate in environments up to 300 °C. Performance is application dependent. Contact our Technical Sales department to discuss your specific application requirements.
Contact Information	For additional information please contact your sales representative. You can also visit our website at www.lightera.com or call 1-888-FIBERHELP (1-888-342-3743) USA or 1-770-798-5555 outside the USA. For a full list of our certifications, visit our website.
Trademark Notice and Disclaimer	Lightera reserves the right to make changes to the product(s) described in this document at any time without notice. This document is for informational purposes only and is not intended to modify or supplement any Lightera warranties or specifications relating to any of its products or services.